

G BRADDOCK BUILDING & PLASTERING CONTRACTOR

45 DOVE WAY, WATERHOUSES, S/O/T, ST103HG

www.braddockbuildingrenovations.co.uk

Richard Murfin
4 Weston Rd
Aston on Trent

Re-plastering with Lime Plaster

Method and specification

Having removed the original plaster, the walls will be brushed down and dampened prior to applying the lime plaster

The three coat lime plaster consists of a scratch coat of haired lime mortar which will be left to dry for approximately 2 -3 weeks then a second coat of un-haired mortar and when dry a finale finish coat of lime putty finish which can be troweled or sponged as required.